


## アルミ化研時間変化(5052材使用)


	Ry	Ra
素材	1.5	0.25
条件1	5.5	0.45
条件2	8.5	0.79
条件3	9.1	0.85
条件4	10	0.91
条件5	10.5	1.07




条件1



条件2



条件3



条件4



条件5



素材

画像CCD1000倍画像

